

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

DB050575/



20
B.G.

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : C08F 4/70, C07F 15/04, C07C 251/20		A1	(11) International Publication Number: WO 98/03559 (43) International Publication Date: 29 January 1998 (29.01.98)
(21) International Application Number: PCT/US97/12801 (22) International Filing Date: 21 July 1997 (21.07.97) (30) Priority Data: 60/022,295 23 July 1996 (23.07.96) US 60/022,796 30 July 1996 (30.07.96) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: MCLAIN, Stephan, James; 202 Old Mill Lane, Wilmington, DE 19803 (US). FELDMAN, Jerald; 16 Cinnamon Drive, Hockessin, DE 19707 (US). (74) Agent: EVANS, Craig, H.; E.I. du Pont de Nemours and Company, Legal Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US).			(81) Designated States: AL, AM, AU, AZ, BA, BB, BG, BR, BY, CA, CN, CU, CZ, EE, GE, HU, IL, IS, JP, KG, KP, KR, KZ, LC, LK, LR, LT, LV, MD, MG, MK, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UZ, VN, YU, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: POLYMERIZATION PROCESSES FOR OLEFINS			
(57) Abstract Certain olefins such as ethylene, α -olefins and cyclopentene can be polymerized by using catalyst system containing a nickel or palladium α -diimine complex, a metal containing hydrocarbylation compound, and a selected Lewis acid, or catalyst system containing certain nickel(II) or palladium(II) compounds, an α -diimine, a metal containing hydrocarbylation compound, and optimally a selected Lewis acid. The process advantageously produces polyolefins useful for molding resins, films, elastomers and other uses.			

10/069,348

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

TITLE

POLYMERIZATION PROCESSES FOR OLEFINS

This application claims the benefit of U.S.
5 Provisional Application No. 60/022,295 (Case No.
CR-9969-P1), filed July 23, 1996, and U.S. Provisional
Application No. 60/022,796 (Case No. CR-9969-P2), filed
July 30, 1996.

10 FIELD OF THE INVENTION

Disclosed herein are processes for polymerizing
selected olefins, by contacting them with certain
nickel or palladium compounds, other selected
compounds, and if the nickel or palladium compound is
15 not already an α -diimine complex, a free α -diimine.


TECHNICAL BACKGROUND

Polyolefins are important items of commerce, many
thousands of tons being produced annually. They are
useful in many applications depending upon their
20 particular properties, for instance as molding resins,
fibers, films useful in packaging and/or electronics,
elastomers, and many others. There are many known
polymerization processes for producing polyolefins, but
given the importance of these polymers, improved
25 processes are constantly being sought.

L. K. Johnson, et. al., J. Am. Chem. Soc., vol.
117, p. 6414-6415 (1995), and L. K. Johnson, et al.,
J. Am. Chem. Soc., vol. 118, p. 267-268 (1996) describe
the polymerization of olefins using certain α -diimine
30 complexes. Neither of these references describes a
polymerization process using the starting materials
described herein.

SUMMARY OF THE INVENTION

Described herein is a first process for the
35 polymerization of olefins, comprising, contacting, at a
temperature of about -100°C to about $+200^{\circ}\text{C}$, a Ni(II)
or Pd(II) complex of (I),



(I)

a metal containing hydrocarbylation compound, and a compound (II) selected from the group consisting of
 5 $B(C_6F_5)_3$, $AlCl_3$, $AlBr_3$, $Al(OTf)_3$, and $(R^{13}R^{14}R^{15}C)Y$, with an olefin, wherein:

said olefin is selected from the group consisting of ethylene, an olefin of the formula $R^{17}CH=CH_2$ or $R^{17}CH=CHR^{17}$, cyclobutene, cyclopentene, and
 10 a norbornene;

R^2 and R^5 are each independently aryl or substituted aryl, provided in both R^2 and R^5 at least one of the carbon atoms bound to a carbon atom bound directly to an imino nitrogen atom does not have any
 15 hydrogen atoms bound to it;


R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

20 R^{13} , R^{14} and R^{15} are each independently aryl or substituted aryl;

each R^{17} is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic
 25 bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms; and

Y is a relatively noncoordinating anion.

This invention also concerns a second process for the polymerization of olefins, comprising, contacting a
 30 $Ni(II)$ or $Pd(II)$ salt with (I),



(I)

a metal containing hydrocarbylation compound, and optionally a compound (II) selected from the group
 5 consisting of $\text{B}(\text{C}_6\text{F}_5)_3$, AlCl_3 , AlBr_3 , $\text{Al}(\text{OTf})_3$, and $(\text{R}^{13}\text{R}^{14}\text{R}^{15}\text{C})\text{Y}$, with an olefin, wherein:

said Ni(II) or Pd(II) salt is selected from the group consisting of $\text{Ni}(\text{O}_2\text{CR}^7)_2$, $\text{Ni}[\text{R}^8\text{COCH}=\text{C}(\text{O})\text{R}^8]_2$, NiX_2 , $\text{L}^1\text{L}^2\text{NiX}_2$, $\text{Ni}(\text{OR}^{18})_2$, $\text{Pd}(\text{O}_2\text{CR}^9)_2$,
 10 $\text{Pd}[\text{R}^{10}\text{COCH}=\text{C}(\text{O})\text{R}^{10}]_2$, PdX_2 , $\text{L}^1\text{L}^2\text{PdX}_2$, and $\text{Pd}(\text{OR}^{19})_2$;

said olefin is selected from the group consisting of ethylene, an olefin of the formula $\text{R}^{17}\text{CH}=\text{CH}_2$ or $\text{R}^{17}\text{CH}=\text{CHR}^{17}$, cyclobutene, cyclopentene, and a norbornene;

15 R^2 and R^5 are each independently aryl or substituted aryl, provided in both R^2 and R^5 at least one of the carbon atoms bound to a carbon atom bound directly to an imino nitrogen atom does not have any hydrogen atoms bound to it;

20 R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

R^{13} , R^{14} and R^{15} are each independently aryl or
 25 substituted aryl;

each R^{17} is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at
 30 least two saturated carbon atoms; and

each R^{18} and R^{19} is independently hydrocarbyl, substituted hydrocarbyl, or $\text{R}^{21}\text{SO}_3^-$;

each R^7 , R^8 , R^9 and R^{10} is independently hydrocarbyl or substituted hydrocarbyl containing from 1 to 20 carbon atoms;


5 each X is independently halogen or $R^{21}SO_3^-$;
each R^{21} is independently aryl, substituted aryl or perfluoroalkyl;

L^1 and L^2 are ligands capable of being displaced by (I), or taken together are a bidentate
10 ligand that is capable of being displaced by (I); and

Y is a relatively noncoordinating anion;


and provided that when said hydrocarbylation compound is other than an alkylaluminum compound containing one or more halogen atoms bound to an aluminum atom or $(R^{20}AlO)_q$ wherein R^{20} is alkyl and q is
15 a positive integer, (II) must be present.

Described herein is a novel compound of the formula



20 wherein each X is independently halogen, R^7CO_2 , $R^8COCH=C(O)R^8$, or OR^{18} , each R^{18} is independently hydrocarbyl, and R^7 , R^8 are hydrocarbyl or substituted hydrocarbyl containing from 1 to 20 carbon atoms.

Also disclosed is a compound of the formula



(VII).

DETAILS OF THE INVENTION


Herein certain terms are used to define certain chemical groups or compounds. These terms are defined below.

5 • A "hydrocarbyl group" is a univalent group containing only carbon and hydrogen. If not otherwise stated, it is preferred that hydrocarbyl groups herein contain 1 to about 30 carbon atoms.

 • By "substituted hydrocarbyl" herein is meant
10 a hydrocarbyl group which contains one or more substituent groups which are inert under the process conditions to which the compound containing these groups is subjected. The substituent groups also do not substantially interfere with the process. If not
15 otherwise stated, it is preferred that substituted hydrocarbyl groups herein contain 1 to about 30 carbon atoms. Included in the meaning of "substituted" are heteroaromatic rings.

 • By an alkyl aluminum compound is meant
20 a compound in which at least one alkyl group is bound to an aluminum atom. Other groups such as alkoxide, oxygen, and halogen may also be bound to aluminum atoms in the compound.

 • By "hydrocarbylene" herein is meant a
25 divalent group containing only carbon and hydrogen. Typical hydrocarbylene groups are $-(CH_2)_4-$, $-CH_2CH(CH_2CH_3)CH_2CH_2-$ and




(An)

30 If not otherwise stated, it is preferred that hydrocarbylene groups herein contain 1 to about 30 carbon atoms.

 • By "substituted hydrocarbylene" herein is meant a hydrocarbylene group which contains one or more
35 substituent groups which are inert under the process

conditions to which the compound containing these groups is subjected. The substituent groups also do not substantially interfere with the process. If not otherwise stated, it is preferred that substituted hydrocarbylene groups herein contain 1 to about 30 carbon atoms. Included within the meaning of "substituted" are heteroaromatic rings.


• By "a norbornene" is meant that the monomer is characterized by containing at least one norbornene-functional group in its structure including norbornadiene as identified by the formulas below, which can be substituted or unsubstituted




(XXXIV)

wherein "a" represents a single or double bond.

Representative monomers are compounds (XXXV) and (XXXX) as follows:



(XXXV);



(XXXX)

wherein R^{46} , R^{47} , R^{48} , and R^{49} independently are hydrogen halogen, or hydrocarbyl, provided that, except if the hydrocarbyl group is vinyl, if any of the hydrocarbyl are alkenyl, there is no terminal double bond, i.e., the double bond is internal; or R^{46} and R^{48} taken together can be part of carbocyclic ring (saturated, unsaturated or aromatic); or R^{46} and R^{47} and/or R^{48} and R^{49} taken together are an alkylidene group. In these structures "z" is 1 to 5.

Examples of such norbornenes include norbornadiene, 2-norbornene, 5-methyl-2-norbornene, 5-hexyl-2-norbornene, 5-ethylidene-2-norbornene, vinylnorbornene, dicyclopentadiene, dihydrodicyclopentadiene, tetracyclododecene, trimers of cyclopentadiene, halogenated norbornenes wherein

R^{46} , R^{47} , R^{48} and R^{49} may also be halogen or fully halogenated alkyl groups such as C_wF_{2w+1} wherein w is 1 to 20, such as perfluoromethyl and perfluorodecyl.

5 The halogenated norbornenes can be synthesized via the Diels-Alder reaction of cyclopentadiene an appropriate dieneophile, such as $F_3CC\equiv CCF_3$ or $R^{49}_2C=CR^{49}C_wF_{2w+1}$ wherein each R^{49} is independently hydrogen or fluorine and w is 1 to 20.

10 • By "saturated hydrocarbyl" is meant a univalent group containing only carbon and hydrogen which contains no unsaturation, such as olefinic, acetylenic, or aromatic groups. Examples of such groups include alkyl and cycloalkyl. If not otherwise
15 stated, it is preferred that saturated hydrocarbyl groups herein contain 1 to about 30 carbon atoms.

 • By "aryl" is meant a monovalent radical which is one or more carbocyclic aromatic rings, and wherein the free bond is to a carbon atom of an
20 aromatic ring. By "substituted aryl" is meant an aryl group substituted with one or more substituents which do not interfere with the polymerization reaction. Phenyl is a preferred aryl group for R^{13} , R^{14} and R^{15} .

 • Herein the group "OTf" means a
25 perfluoroalkylsulfonate anion containing 1 to 20 carbon atoms. A preferred perfluoroalkylsulfonate anion is trifluoromethanesulfonate (sometimes "triflate").

 • By " α -olefin" is meant a compound of the formula $CH_2=CHR^{19}$, wherein R^{19} is n-alkyl or branched n-alkyl, preferably n-alkyl.
30

 • By "linear α -olefin" is meant a compound of the formula $CH_2=CHR^{19}$, wherein R^{19} is n-alkyl. It is preferred that the linear α -olefin have 4 to 40 carbon atoms.

35 • By a "saturated carbon atom" is meant a carbon atom which is bonded to other atoms by single bonds only. Not included in saturated carbon atoms are carbon atoms which are part of aromatic rings.

- By a quaternary carbon atom is meant a saturated carbon atom which is not bound to any hydrogen atoms. A preferred quaternary carbon atom is bound to four other carbon atoms.

5 • By an olefinic bond is meant a carbon-carbon double bond, but does not include bonds in aromatic rings.

10 • By a "polymerization process" herein (and the polymers made therein) is meant a process which produces a polymer with a degree of polymerization (DP) of about 20 or more, preferably about 40 or more. By "DP" is meant the average number of repeat (monomer) units in the polymer.

15 • By a metal containing hydrocarbylation compound is meant a compound which can transfer a hydrocarbyl group to a nickel or palladium compound. One form of this compound is commonly called an alkylating agent or compound in organic chemistry. Generally the hydrocarbyl group is thought of being
20 present in the compound as an anion. Useful alkylating agents have the formula $MX_mR_n^6$ or $[Al(O)R^{11}]_q$, wherein M is a metal, preferably Li, Mg, Zn[II], Al, or Sn[IV]; each X is independently F, Cl, Br, I, or OR^{12} ; each R^6 is independently hydrocarbyl containing from 1 to 20
25 carbon atoms; m is zero or greater and n is 1 or greater, and m+n is the valence of M and if the valence of M is 1, then m is 0; R^{11} and R^{12} are each independently hydrocarbyl, preferably alkyl, containing 1 to 20 carbon atoms; and q is a positive integer. It
30 is preferred that R^{11} is methyl.

 • By a weakly coordinating anion herein is meant an anion that does not coordinate strongly to a nickel or palladium cationic complex. The coordinating ability of such anions is known and has been discussed
35 in the literature, see for instance W. Beck., et al., Chem. Rev., vol. 88 p. 1405-1421 (1988), and S. H. Strauss, Chem. Rev., vol. 93, p. 927-942 (1993), both of which are hereby included by reference. In

addition to these "traditional" weakly coordinating anions, heterogeneous anions may also be employed. In these cases, the true nature of the counterion is poorly defined or unknown. A wide variety of heterogeneous inorganic materials can be made to function as non-coordinating counterions. Examples include aluminas, silicas, silica/aluminas, cordierites, clays, $MgCl_2$, and many others utilized as traditional supports for Ziegler-Natta olefin polymerization catalysts. These are generally materials which have Lewis or Bronsted acidity. High surface area is usually desired and often these materials will have been activated through some heating process. Heating may remove excess surface water and change the surface acidity from Bronsted to Lewis type. Materials which are not active in the role may often be made active by surface treatment. For instance, a surface-hydrated silica, zinc oxide or carbon can be treated with an alkylaluminum compound to provide the required functionality.

Preferred relatively noncoordinating anions are BAF , BF_4 , SbF_6 , $B(C_6F_5)_4$ and PF_6 . Herein BAF is an abbreviation for the tetrakis[3,5-bis(trifluoromethyl)phenyl]borate.

It is preferred that each R^{18} and R^{19} is independently hydrocarbyl, each R^7 , R^8 , R^9 and R^{10} is independently hydrocarbyl, and/or each X is independently halogen, more preferably chlorine or bromine. When present it is preferred that R^{21} is trifluoromethanesulfonate, phenyl or tolyl.

In both of the polymerization processes described herein compound (I) or a complex of it is present initially. In (I) R^2 and R^5 are each independently aryl or substituted aryl, provided in both R^2 and R^5 at least one of the carbon atoms bound to a carbon atom bound directly to an imino nitrogen atom does not have any hydrogen atoms bound to it. In practice this means that in R^2 and R^5 the carbon atom ortho or adjacent to

the carbon atom which is bound to an imino nitrogen atom must be substituted. Suitable groups for R^2 and R^5 include 2-methylphenyl, 2-phenylphenyl, 2,6-diisopropylphenyl, 1-naphthyl, 1-methyl-2-naphthyl, 1-anthracenyl, and 9-anthracenyl. Aryl groups that are not suitable include phenyl, 2-naphthyl, and 3-ethylphenyl.

Preferred combinations of groups for R^2 , R^3 , R^4 , and R^5 are given in the following Table.

R ²	R ³	R ⁵	R ⁵
2,6-i-PrPh	H	H	2,6-i-PrPh
2,6-i-PrPh	Me	Me	2,6-i-PrPh
2,6-i-PrPh	An	An	2,6-i-PrPh
2,6-MePh	H	H	2,6-MePh
2,6-i-PrPh	Me	Me	2,6-i-PrPh
2,6-i-PrPh	H	H	2,6-i-PrPh
2,6-MePh	H	H	2,6-MePh
2,6-i-PrPh	H	H	2,6-i-PrPh
2,6-i-PrPh	Me	Me	2,6-i-PrPh
2,6-MePh	H	H	2,6-MePh
2,6-EtPh	Me	Me	2,6-EtPh
2,4,6-MePh	Me	Me	2,4,6-MePh
2,6-MePh	Me	Me	2,6-MePh
2,6-i-PrPh	An	An	2,6-i-PrPh
2,6-MePh	An	An	2,6-MePh
2-t-BuPh	An	An	2-t-BuPh
2,5-t-BuPh	An	An	2,5-t-BuPh
2,4,6-MePh	An	An	2,4,6-MePh
2-Cl-6-MePh	Me	Me	2-Cl-6-MePh
2,6-Cl-4-OMePh	Me	Me	2,6-Cl-4-OMePh
2,6-Cl-4-OMePh	An	An	2,6-Cl-4-OMePh
2-i-Pr-6-MePh	An	An	2-i-Pr-6-MePh
2-i-Pr-6-MePh	Me	Me	2-i-Pr-6-MePh
2,6-t-BuPh	H	H	2,6-t-BuPh
2,6-t-BuPh	Me	Me	2,6-t-BuPh
2,6-t-BuPh	An	An	2,6-t-BuPh
2-t-BuPh	Me	Me	2-t-BuPh

Herein Me is methyl, Et is ethyl, Pr is propyl, Bu is butyl, Ph is phenyl, OMe is methoxy, and An is 1,8-naphthylidene.

Any of the groups shown in the above table may also be mixed in any fashion to achieve other combinations.

- 5 In certain situations "unsymmetrical" α -diimine ligands of formula (I) are also preferred. In particular when R² and R⁵ are phenyl, and one or both of these is substituted in such a way as different sized groups are present in the 2 and 6 position of the

phenyl ring(s) unusual polymers may be produced, for instance if one or both of R^2 and R^5 are 2-t-butylphenyl. In this context when R^2 and/or R^5 are "substituted" phenyl the substitution may be not only in the 2 and/or 6 positions, but on any other position in the phenyl ring. For instance, 2,5-di-t-butylphenyl, and 2-t-butyl-4,6-dichlorophenyl would be included in substituted phenyl.

The steric effect of various groupings has been quantified by a parameter called E_s , see R. W. Taft, Jr., J. Am. Chem. Soc., vol. 74, p. 3120-3128, and M. S. Newman, Steric Effects in Organic Chemistry, John Wiley & Sons, New York, 1956, p. 598-603. For the purposes herein, the E_s values are those for o-substituted benzoates described in these publications. If the value for E_s for any particular group is not known, it can be determined by methods described in these publications. For the purposes herein, the value of hydrogen is defined to be the same as for methyl. It is preferred that difference in E_s , when R^2 (and preferably also R^5) is phenyl, between the groups substituted in the 2 and 6 positions of the phenyl ring is at least 0.15, more preferably at least about 0.20, and especially preferably about 0.6 or more. These phenyl groups may be unsubstituted or substituted in any other manner in the 3, 4 or 5 positions. These differences in E_s are preferred in (I), and in both of the polymerization processes herein.


It will be understood by the artisan that not every possible compound (I) or its Ni or Pd complex will be active in polymerizations of every olefin listed herein, but that the vast majority will be active in such polymerizations. Special steric or electronic features in (I) combined with the structure of the olefin may prevent polymerization in a few cases. However the determination of whether a particular α -diimine or its Ni or Pd complex will be active in polymerization with a certain olefin requires

minimal experimentation to determine, see for instance the polymerization Examples herein.


Preferred olefins in both polymerizations are one or more of ethylene, propylene, 1-butene, 2-butene, 1-hexene 1-octene, 1-pentene, 1-tetradecene, norbornene, and cyclopentene, with ethylene, propylene and cyclopentene being more preferred. Ethylene and cyclopentene (alone as homopolymers) are especially preferred. Another preferred type of olefin is an α -olefin, and a linear α -olefin is especially preferred. When norbornene is used as a monomer it is preferred that it be the only olefin present.

Random copolymers may be made with these polymerization processes by the simultaneous polymerization of 2 or more olefins. Block copolymers may be made (particularly at subambient temperatures, preferably about -30°C to 0°C) by sequential polymerization of the monomer(s) of each block in the polymer.

It has been found that compound 4,



when used for polymerization of cyclopentene, gives a tractable cyclopentene with the highest melting point yet achieved. X is preferably chlorine or bromine. This compound may be used in the first polymerization process. It is made from compound (VII), or (VII) may be used directly in the second polymerization process.



(VII).


In both 4 and (VII) the methoxy group may be replaced
 5 by an alkoxy group wherein the alkoxy group contains 2
 to 20 carbon atoms.

The temperature at which the polymerization
 processes are carried out is about -100°C to about
 $+200^{\circ}\text{C}$, preferably about 0°C to about 150°C , more
 10 preferably about 25°C to about 100°C . The pressure at
 which the polymerization is carried out (for a gaseous
 monomer) is not critical, atmospheric pressure to about
 275 MPa being a suitable range. The pressure can
 affect the microstructure of the polyolefin produced.

15 A preferred compound (II) is $(\text{C}_6\text{F}_5)_3\text{B}$. When (II)
 is $(\text{R}^{13}\text{R}^{14}\text{R}^{15}\text{C})\text{Y}$ it is preferred that all of R^{13} , R^{14} and
 R^{15} are phenyl. It will be understood by the artisan
 that (II) is preferably a Lewis acid-type compound.

In the second polymerization process, when a
 20 hydrocarbylation compound is other than an
 alkylaluminum compound containing one or more halogen
 atoms bound to an aluminum atom or an alkyl
 aluminoxane, (II) must be present. Thus when the
 hydrocarbylation compound is R_3Al (II) must be present.
 25 When the hydrocarbylation compound is R_2AlBr , RAlCl_2 ,
 or "RAlO", (II) may optionally be present (R in these
 last two sentences is alkyl).

In the first process, when a $\text{Ni}[\text{II}]$ or $\text{Pd}[\text{II}]$
 complex of (I) is used, a preferred structure for the
 30 complex is



(VI)

wherein M is Ni or Pd, R², R³, R⁴ and R⁵ are as defined
 5 as above and T¹ and T² are each independently halogen,
 R⁷CO₂, R⁸COCH=C(O)R⁸, OR¹⁸ wherein R⁷, R⁸ and R¹⁸ are as
 defined above. It is preferred that T¹ and T² are
 chlorine and/or bromine.

In both polymerization processes, molar ratios of
 10 the various ingredients are not critical, but for good
 yields of polymer and/or to minimize cost of
 ingredients, certain ratios are preferred. In the
 first polymerization process it is preferred that the
 ratio of number of moles of olefin:"moles" of Pd or Ni
 15 present be greater than 3,000, preferably about 5,000
 or more. The molar ratio of (II):Pd or Ni is
 preferably about 0.5 to about 10, more preferably about
 1 to about 5. The molar ratio of hydrocarbylation
 compound: Pd or Ni is preferably about 0.5 to about 200,
 20 more preferably about 20 to about 100, in the second
 polymerization process when (II) is not present. In
 the first polymerization process, or in the second
 polymerization process when (II) is present, the molar
 ratio of hydrocarbylation compound: Pd or Ni is
 25 preferably about 0.5 to about 20, more preferably about
 1 to about 10.

When the ingredients for the polymerization are
 first mixed to initiate the polymerization it is
 preferred that they be mixed in a liquid medium,
 30 preferably a liquid medium in which at least one of the
 ingredients other than the olefin is at least slightly
 soluble. For instance the polymerization of
 cyclopentene may be carried out in neat cyclopentene or
 in a mixture of 1,2,4-trichlorobenzene and

cyclopentene. The polymerization itself may then be carried out in solution (the polymer soluble in the

medium), slurry, or even the gas phase with droplets containing the active catalyst suspended in, for example, gaseous olefin.

The polymerization may be carried out in any of the usual ways, such as a batch, semi-batch or continuous operation. The latter for example may be a continuous stirred tank reactor, which is well known in the art.

These polymerization processes have advantages over those processes reported in L. K. Johnson, et al., J. Am. Chem. Soc., vol. 117, p. 6414-6415 (1995), and L. K. Johnson, et al., J. Am. Chem. Soc., vol. 118, p. 267-268 (1996). For the first polymerization process, the presence of (II) reduces the amount of alkylaluminum compound that must be added to the process to achieve good polymer yields, and/or the Ni or Pd compound which is used is relatively stable and therefore may be stored for long periods and/or used under ambient conditions (e.g. no refrigeration needed). In addition to the advantages described for the first polymerization process, the second polymerization does not require the prior preparation of a complex of Ni or Pd with (I), but rather the Ni or Pd compounds used are readily available and relatively stable. Not having to prepare the Ni or Pd complex of (I) in a separate step is also economically advantageous.

In the Examples, the following abbreviations are used:

DSC - differential scanning calorimetry
Et - ethyl
Me - methyl
MMAO - modified methyl aluminoxane
OAc - acetate
Pr - propyl
Tg - glass transition temperature
Tm - melting point

Examples

Cyclopentene was purified by passage through a column of 5 Å molecular sieves, followed by passage through a column of alumina, and finally distillation under nitrogen from sodium metal.

Modified Methyl Aluminoxane [(MeAlO)_n] used in these experiments was purchased from Akzo as a 6.7 wt.% solution in toluene. The methyl aluminoxane has been modified by replacing about 25 mole percent of the methyl groups with isobutyl groups.

Examples 1-18 and Comparative Examples A-L

The following general procedure was used with compounds 1-6 below. In a nitrogen filled dry box, the catalyst was suspended in cyclopentene (molar ratio = 10,000:1 unless otherwise noted). (II) and hydrocarbylation compound (HCC) were then added in rapid succession; molar ratios based on nickel or palladium are noted in Table 1. Unless otherwise noted, (II) was added to the reaction mixture before the HCC. The resulting mixture was stirred at ambient temperature under nitrogen; in some instances, due to the amount of precipitated polymer it was impossible to stir the reaction for more than a few days. After the number of days indicated in Table 1, the reaction was quenched and the polymer completely precipitated by addition of methanol. The polymer was then washed with methanol/HCl and then acetone on a fritted filter, and dried. The total turnover number for each reaction (moles cyclopentene polymerized per mole of Ni or Pd) is indicated in Table 1.

It can be seen from Table 1 that addition of (II) such as B(C₆F₅)₃ and AlCl₃ allows for the successful use of alkylating agents such as AlMe₃, AlEt₃, Al(OEt)Et₂, and ZnEt₂; in the absence of (II), no product is observed.

DSC data for several examples are compiled in Table 2. In general, the melting points are broad and

the T_m values given represent the approximate end of the melting transition.







123456

Table 1

<u>Example</u>	<u>Ni or Pd</u> <u>Compound</u> <u>d</u>	<u>HCC</u> <u>(equiv)</u>	<u>(II)</u> <u>(equiv)</u>	<u>turn-</u> <u>overs</u> ^a <u>(days)</u>	<u>Melt</u> <u>Index</u> ^b
1	1	EtAlCl ₂ (3)	B(C ₆ F ₅) ₃ (3)	1833 (7)	7.6
2 ^e	1	EtAlCl ₂ (3)	(Ph ₃ C)BF ₄ (3)	1827 (7)	78
A	1	EtAlCl ₂ (50)	-----	1760 (7)	
B	1	EtAlCl ₂ (3)	-----	846 (7)	8.4
3	1	AlEt ₃ (3)	B(C ₆ F ₅) ₃ (3)	3680 (7)	14
C	1	AlEt ₃ (3)	-----	0 (5)	
4	1	AlEt ₃ (3)	AlCl ₃ (50)	6031 (7)	high ^c
5	1	AlEt ₃ (3)	AlCl ₃ (3)	1398 (7)	6.2
6	1	AlEt ₃ (3)	Al(OTf) ₃ (50)	950 (7)	54
7	1	AlEt ₃ (3)	AlBr ₃ (50)	7624 (7)	high ^c
8	1	AlMe ₃ (3)	B(C ₆ F ₅) ₃ (3)	4325 (7)	14
D	1	AlMe ₃ (50)	-----	0 (7)	
9 ^e	1	Al(OEt)Et ₂ (5)	B(C ₆ F ₅) ₃ (5)	4232 (7)	9.6
E	1	Al(OEt)Et ₂ (5)	-----	0 (6)	
10	1	ZnEt ₂ (3)	B(C ₆ F ₅) ₃ (3)	2880 (7)	19
F	1	ZnEt ₂ (3)	-----	0 (8)	
11	2	AlEt ₃ (3)	B(C ₆ F ₅) ₃ (3)	5660 (7)	2.1
G ^g	2	(MeAlO) _n (100)	-----	1195 (5)	7.6
12	2	EtAlCl ₂ (3)	B(C ₆ F ₅) ₃ (3)	3250 (7)	1.7
H ^h	2	EtAlCl ₂ (50)	-----	5230 (8)	3.6
13	2	AlEt ₃ (3)	AlCl ₃ (50)	4718 (7)	high ^c
14 ^e	2	Al(OEt)Et ₂ (5)	B(C ₆ F ₅) ₃ (5)	4688 (7)	2.4
15	3	AlEt ₃ (3)	B(C ₆ F ₅) ₃ (3)	2514 (7)	1.0
I	3	(MeAlO) _n (100)	-----	2020 (7)	
J	3	EtAlCl ₂ (50)	-----	5000 (2)	
16	4	AlEt ₃ (3)	B(C ₆ F ₅) ₃ (3)	3770 (7)	
K	4	EtAlCl ₂ (50)	-----	7210 (7)	
L	4	(MeAlO) _n (100)	-----	845 (7)	
17	5	ZnEt ₂ (3)	B(C ₆ F ₅) ₃ (3)	3462 (7)	0.9 ^f
18	6	AlEt ₃ (3)	B(C ₆ F ₅) ₃ (3)	1243 (7)	low ^d

^a"turnovers" = molar equivalents of monomer polymerized per molar equivalent of Ni or Pd

^bMelt indices were run with 8.5 kg weights at 300°C. MI value in Table 1 is defined as the mass of polymer (in grams) extruded in 10 minutes. The orifice was 2.095 mm in dia. and 8.000 mm long. MI value is inversely related to polymer molecular weight.

^cMelt index value too high to be recorded accurately; indicates relatively low molecular weight polymer.

^dMelt index value too low to be conveniently recorded; indicates relatively high molecular weight.

^eIn this example, the alkylating agent was added to the reaction mixture before the Lewis acid.

^fMI recorded at 275 °C

^gCyclopentene : Ni = 5,000:1


^hCyclopentene : Ni = 15,000:1

Table 2

<u>Example</u>	<u>-T_m(end) °C</u>	<u>ΔH_f (J/g)</u>
1	285	17
2	260	6
B	285	8
3	277	12
6	280	15
9	280	22
10	280	24
11	265	16
12	255	12
H	260	17
14	263	15
15	290	18
I	291	18
J	291	31
16	325	32
K	335	9
17	275	22

Example 19

This example demonstrates the use of $\text{Ni}(\text{acac})_2$ ($\text{acac} = \text{MeCOCH}=\text{C}(\text{O})\text{Me}$) as a precursor for cyclopentene polymerization. In a nitrogen filled glove box, $\text{Ni}(\text{acac})_2$ (4 mg, 0.015 mmol) was dissolved in cyclopentene (10.0 g, 147 mmol) to give a pale, green-blue solution. To this was added **7** (6 mg, 0.015 mmol). To the resulting orange solution was added $\text{B}(\text{C}_6\text{F}_5)_3$ (23 mg, 0.045 mmol) to give a violet solution. Finally, 1.9 M AlEt_3 in toluene (24 μl , 0.045 mmol) was added to the reaction mixture. The resulting magenta solution was stirred at ambient temperature for ~3 days with a magnetic stirbar; at the end of this time the reaction could no longer be stirred due to the amount of polycyclopentene that had precipitated. Seven days after the addition of AlEt_3 , the reaction mixture was quenched and the polymer completely precipitated by addition of methanol under air. The precipitated polymer was washed with methanol/HCl and then acetone, and then dried to afford 4.00 g of polycyclopentene. DSC: $T_m(\text{end}) \approx 290^\circ\text{C}$ (19 J/g). This material was pressed at 300°C to give a clear, tough film.

**7**

25


Comparative Example M

This experiment was identical to Example 19, except that $\text{B}(\text{C}_6\text{F}_5)_3$ was not present. Methanol was added to the reaction mixture after it had stirred at ambient temperature for 7 days; no polycyclopentene precipitated. This demonstrates that (II) $[\text{B}(\text{C}_6\text{F}_5)_3]$ in

19] must be present for activity when AlEt_3 is used as the alkylating agent.

Example 20

This example further demonstrates the use of
5 $\text{Ni}(\text{acac})_2$ as a catalyst precursor. In a nitrogen filled glove box, $\text{Ni}(\text{acac})_2$ (4 mg, 0.015 mmol) and 8 (5 mg, 0.015 mmol) were dissolved in cyclopentene (10.0 g, 147 mmol) to give a pale-yellow solution. To this was added $\text{B}(\text{C}_6\text{F}_5)_3$ (23 mg, 0.045 mmol) followed by 1.9 M
10 AlEt_3 in toluene (24 μl , 0.045 mmol). The resulting orange solution was stirred at ambient temperature for 7 days with a magnetic stirbar. The reaction mixture was then quenched and the polymer completely precipitated by addition of methanol under air. The
15 precipitated polymer was washed with methanol/HCl and then acetone, and then dried to afford 3.19 g of polycyclopentene. DSC: $T_m(\text{end}) \approx 270^\circ\text{C}$ (20 J/g).



8


Example 21

20 This example demonstrates the use of $\text{Ni}[\text{O}_2\text{C}(\text{CH}_2)_6\text{CH}_3]_2$ as a catalyst precursor. In a nitrogen filled glove box, $\text{Ni}[\text{O}_2\text{C}(\text{CH}_2)_6\text{CH}_3]_2$ (5 mg, 0.015 mmol) and 7 (6 mg, 0.015 mmol) were dissolved in
25 cyclopentene (10.0 g, 147 mmol) to give an orange solution. To this was added $\text{B}(\text{C}_6\text{F}_5)_3$ (23 mg, 0.045 mmol) followed by 1.9 M AlEt_3 in toluene (24 μl , 0.045 mmol). The resulting magenta solution was stirred at ambient temperature for 7 days with a magnetic stirbar.
30 The reaction mixture was then quenched and the polymer completely precipitated by addition of methanol under air. The precipitated polymer was washed with

methanol/HCl and then acetone, and then dried afford 1.6 g of polycyclopentene.

Example 22

This example demonstrates the use of $\text{Pd}(\text{OAc})_2$ (OAc is acetate) as a catalyst precursor. In a nitrogen filled glove box, $\text{Pd}(\text{OAc})_2$ (3 mg, 0.013 mmol) and **9** (297 mg, 0.735 mmol) were dissolved in cyclopentene (10.0 g, 147 mmol). To this was added $\text{B}(\text{C}_6\text{F}_5)_3$ (23 mg, 0.045 mmol) followed by 1.9 M AlEt_3 in toluene (24 μl , 0.045 mmol). The resulting cloudy, yellow solution was stirred with a magnetic stirbar at ambient temperature. Twenty-six hours after the addition of AlEt_3 , the reaction mixture was quenched and the polymer completely precipitated by addition of methanol under air. The precipitated polymer was washed with methanol/HCl and then acetone, and then dried to afford 3.48 g of polycyclopentene. DSC: $T_m(\text{end}) = 250^\circ\text{C}$ (24 J/g); $T_g = 100.4^\circ\text{C}$. This material was pressed at 300°C to give a tough film.



9

Example 23

This example demonstrates the synthesis of $\text{ArN}=\text{C}(\text{CH}_3)\text{C}(\text{CH}_3)=\text{NAr}$ (Ar = 2,6-dichloro-4-methoxyphenyl). 2,6-dichloro-4-methoxyaniline (0.767 g, 4 mmol) and biacetyl (0.172 g, 2 mmol) were combined in 10 mL of anhydrous methanol containing 2 drops of concentrated sulfuric acid. After 48 hours, the precipitated product was isolated by filtration, washed with a 10:1 hexane/methanol mixture and dried in vacuo to give 0.476 g solid (55% yield). ^1H NMR (CD_2Cl_2 , 300

MHz): 2.1 (s, -CH₃, 6 H); 3.8 (s, -OCH₃, 6H); 7.0 (s, aromatic H, 4H).

Example 24

This example demonstrates the preparation of
5 (ArN=C(CH₃)C(CH₃)=NAr)NiBr₂ (Ar = 2,6-dichloro-4-methoxyphenyl), 3. ArN=C(CH₃)C(CH₃)=NAr (Ar = 2,4,6-trimethylphenyl) (0.132g, 0.304 mmol) was combined with NiBr₂(1,2-dimethoxyethane) (0.094g, 0.304 mmol) in 4.6 mL of anhydrous methylene chloride under nitrogen in a
10 dry box. After stirring for 168 hours, the solvent was decanted from the dark purple crystalline product. The product was washed 3X with pentane and dried in vacuo.

Example 25

This example demonstrates the preparation of
15 ArN=C(An)C(An)=NAr (Ar = 2,6-dichloro-4-methoxyphenyl). 2,6-dichloro-4-methoxyaniline (2.18 g, 11.35 mmol) and acenapthenequinone (1.03 g, 5.63 mmol) were combined in 20 mL of anhydrous methanol containing 3 drops of concentrated sulfuric acid. After 48 hours, the
20 precipitated product was isolated by filtration, washed with hexane followed by methanol, and dried in vacuo to give 2.47 g solid. ¹H NMR showed this product to be a 3:1 mixture of the desired diimine and the monoimine. A portion of this solid (1.89 g) was combined with 0.42
25 g (2.19 mmol) additional 2,6-dichloro-4-methoxyaniline in a mixture of methanol (20 mL) and chloroform (5 mL) containing 2 drops of formic acid. The mixture was refluxed for 6 hours and then cooled to 25°C overnight. The precipitated product was isolated by filtration,
30 washed with hexane followed by methanol, and dried in vacuo to give 1.70 g solid. TLC showed this to be a mixture of two compounds. A portion of the solid (1.50 g) was purified by column chromatography on silica gel 60. The crude material was loaded on the column as a
35 chloroform solution, and then eluted with toluene. The first band (0.96 g after solvent evaporation) was the desired diimine. ¹H NMR (CD₂Cl₂, 300 MHz):
3.77, 3.80, 3.88 (singlets, -OMe, total area = 6.1 H);

6.8 - 8.3 (aromatic H, total area = 9.9H). The three methoxy peaks are consistent with isomers due to slow rotation about the N=C bond on the NMR time scale.

Example 26

5 This example demonstrates the preparation of
(ArN=C(An)C(An)=NAr)NiBr₂ (Ar = 2,6-dichloro-4-methoxyphenyl), **4**. ArN=C(An)C(An)=NAr (Ar = 2,6-dichloro-4-methoxyphenyl) (0.23 g) was combined with NiBr₂(1,2-dimethoxyethane) (0.136 g) in 7.5 mL of
10 anhydrous methylene chloride. The reaction was shaken for 24 hours. About 2/3 of the solvent was removed by evaporation. The precipitated product was isolated by filtration on a fritted glass filter, washed with pentane on the filter, and dried in vacuo.

Example 27

15 This example demonstrates the synthesis of ArN=C(CH₃)C(CH₃)=NAr (Ar = 2-chloro-6-methylphenyl), which was used to synthesize catalyst **2**. 2-Chloro-6-methylaniline (5.66 g, 40.0 mmol) biacetyl (1.72 g, 20.0 mmol) were dissolved in methanol (10 mL). To this
20 was added 2-3 drops of formic acid. The mixture was brought to reflux for 8-9 h. Solvent was then removed to afford an oil. The oil was purified by chromatography on a silica gel column. The first band,
25 after solvent removal, crystallized to give a light yellow solid. The solid was washed with small amount of methanol and vacuum dried to afford 0.5 g of product (7.5%) ¹H NMR (CDCl₃): 7.3 (d, 2H); 7.15 (d, 2H); 6.98 (t, 2H); 2.10 (m, 12H).

30 **2** was prepared from (dimethoxyethane)NiBr₂ and the above ligand, in a manner analogous to that described in examples 24 and 26.

Example 28


 This Example demonstrates the synthesis of
35 ArN=C(CH₃)C(CH₃)=NAr (Ar = 2-chloro-4,6-dimethylphenyl), which was used to synthesize **5**. 2-Chloro-4,6-dimethylaniline (12.45 g, 80.0 mmol) and biacetyl (3.44 g, 40.0 mmol) were dissolved in methanol

(10 mL). To this was added 2-3 drops of formic acid. The mixture was brought to reflux for overnight. Solvent was then removed to afford an oil. The oil was purified by chromatography on a silica gel column. The first band, after solvent removal, crystallized to give a yellow solid which was identified as the desired product (0.71 g, %). ^1H NMR (CDCl_3): 7.10 (s, 2H); 6.95 (s, 2H); 2.30 (s, 6H); 2.10 (s, 6H); 2.07 (s, 6H).

5 was prepared from (dimethoxyethane) NiBr_2 and the above ligand, in a manner analogous to that described in Examples 24 and 26.

Example 29

This example further demonstrates the use of $\text{Pd}(\text{OAc})_2$ as a catalyst precursor. In a nitrogen filled glove box, $\text{Pd}(\text{OAc})_2$ (3 mg, 0.013 mmol) and 10 (256 mg, 0.735 mmol) were dissolved in cyclopentene (10.0 g, 147.0 mmol). To this was added $\text{B}(\text{C}_6\text{F}_5)_3$ (23 mg, 0.045 mmol) followed by 1.9 M AlEt_3 in toluene (24 μl , 0.045 mmol). The reaction mixture was stirred by a magnetic stirbar at ambient temperature for approximately 5 h, after which time it could no longer be stirred due to the amount of precipitated polymer. Seven days after the addition of AlEt_3 , the reaction mixture was quenched and the polymer completely precipitated by addition of methanol under air. The precipitated polymer was washed with methanol/ HCl and then acetone, and then dried to afford 1.99 g of polycyclopentene. Melt Index on this sample under the same conditions as described in Table 1 was 0.37.




10

Example 30

This example demonstrates the use of $\text{Pd}(\text{OAc})_2$ as a catalyst precursor, in the presence of MMAO as the hydrocarbylation compound. In a nitrogen filled glove box, $\text{Pd}(\text{OAc})_2$ (3 mg, 0.013 mmol) and 10 (256 mg, 0.735 mmol) were dissolved in cyclopentene (10.0 g, 147.0 mmol). To this was added 6.7 wt. % MMAO in toluene (0.700 mL, 1.47 mmol). The reaction mixture was stirred at ambient temperature for seven days. The reaction mixture was then quenched and the polymer completely precipitated by addition of methanol under air. The precipitated polymer was washed with methanol/HCl and then acetone, and then dried to afford 0.47 g of polycyclopentene. Melt Index on this sample under the same conditions as described in Table 1 was 16.

Example 31

This example further demonstrates the use of $\text{Pd}(\text{OAc})_2$ as a catalyst precursor. In a nitrogen filled glove box, $\text{Pd}(\text{OAc})_2$ (3 mg, 0.013 mmol) and 11 (116 mg, 0.334 mmol) were dissolved in cyclopentene (10.0 g, 147.0 mmol). To this was added $\text{B}(\text{C}_6\text{F}_5)_3$ (23 mg, 0.045 mmol) followed by followed by 1.9 M AlEt_3 in toluene (24 μl , 0.045 mmol). The reaction mixture was stirred by a magnetic stirbar at ambient temperature; after several hours it could no longer be stirred due to the amount of precipitated polymer. Three days after the addition of AlEt_3 , the reaction mixture was quenched and the polymer completely precipitated by addition of methanol under air. The precipitated polymer was washed with methanol/HCl and then acetone, and then dried to afford 3.36 g of polycyclopentene.



11

Example 32

This example demonstrates the use of Pd(acac)₂ [acac = MeCOCH=C(O)Me] as a catalyst precursor. In a nitrogen filled glove box, Pd(acac)₂ (4-5 mg, 0.015 mmol) and 11 (128 mg, 0.368 mmol) were dissolved in cyclopentene (10.0 g, 147.0 mmol). To this was added B(C₆F₅)₃ (23 mg, 0.045 mmol) followed by followed by 1.9 M AlEt₃ in toluene (24 µl, 0.045 mmol). The reaction mixture was stirred by a magnetic stirbar at ambient temperature; after five hours it could no longer be stirred due to the amount of precipitated polymer. Three days after the addition of AlEt₃, the reaction mixture was quenched and the polymer completely precipitated by addition of iso-propanol and methanol under air. The precipitated polymer was washed with methanol/HCl and then acetone, and then dried to afford 4.84 g of polycyclopentene.

Example 33

This example demonstrates polymerization of 1-hexene. In a nitrogen filled glovebox, 6 (28 mg, 0.048 mmol) was suspended in 1-hexene (2.00 g, 23.8 mmol). To this was added B(C₆F₅)₃ (73 mg, 0.14 mmol) followed by followed by 1.9 M AlEt₃ in toluene (75 µl, 0.14 mmol). The reaction mixture became noticeably warm and viscous upon addition of AlEt₃. The reaction mixture was stirred overnight and then quenched by addition of iso-propanol under air. The polymer was completely precipitated by addition of methanol/HCl, and dried to afford 0.69 g of poly(1-hexene) as an extremely viscous oil. Olefin end-groups could not be detected in the

room temperature ^1H NMR spectrum of the polymer
recorded in CDCl_3 .


Comparative Example N

This example was identical to Example 33, except
5 that $\text{B}(\text{C}_6\text{F}_5)_3$ was not present. Methanol was added to
the reaction mixture after it had stirred at ambient
temperature overnight; no poly(1-hexene) precipitated.
This demonstrates that in this reaction (II) must be
present for activity when AlEt_3 is used as the
10 alkylating agent.

CLAIMS

What is claimed is:

1. A process for the polymerization of olefins, comprising, contacting, at a temperature of about
 5 -100°C to about +200°C, a Ni(II) or Pd(II) complex of (I),



(I)

- a metal containing hydrocarbylation compound, and a
 10 compound (II) selected from the group consisting of $\text{B}(\text{C}_6\text{F}_5)_3$, AlCl_3 , AlBr_3 , $\text{Al}(\text{OTf})_3$, and $(\text{R}^{13}\text{R}^{14}\text{R}^{15}\text{C})\text{Y}$, with an olefin, wherein:

- said olefin is selected from the group consisting of ethylene, an olefin of the formula
 15 $\text{R}^{17}\text{CH}=\text{CH}_2$ or $\text{R}^{17}\text{CH}=\text{CHR}^{17}$, cyclobutene, cyclopentene, and a norbornene;

- R^2 and R^5 are each independently aryl or substituted aryl, provided in both R^2 and R^5 at least one of the carbon atoms bound to a carbon atom bound
 20 directly to an imino nitrogen atom does not have any hydrogen atoms bound to it;


- R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted
 25 hydrocarbylene to form a carbocyclic ring;

R^{13} , R^{14} and R^{15} are each independently aryl or substituted aryl;

- each R^{17} is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond
 30 in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms; and

Y is a relatively noncoordinating anion.

2. A process for the polymerization of olefins, comprising, contacting a Ni(II) or Pd(II) salt with (I),



(I)

a metal containing hydrocarbylation compound, and optionally a compound (II) selected from the group consisting of $\text{B}(\text{C}_6\text{F}_5)_3$, AlCl_3 , AlBr_3 , $\text{Al}(\text{OTf})_3$, and $(\text{R}^{13}\text{R}^{14}\text{R}^{15}\text{C})\text{Y}$, with an olefin, wherein:

said Ni(II) or Pd(II) salt is selected from the group consisting of $\text{Ni}(\text{O}_2\text{CR}^7)_2$, $\text{Ni}[\text{R}^8\text{COCH}=\text{C}(\text{O})\text{R}^8]_2$, NiX_2 , $\text{L}^1\text{L}^2\text{NiX}_2$, $\text{Ni}(\text{OR}^{18})_2$, $\text{Pd}(\text{O}_2\text{CR}^9)_2$, $\text{Pd}[\text{R}^{10}\text{COCH}=\text{C}(\text{O})\text{R}^{10}]_2$, PdX_2 , $\text{L}^1\text{L}^2\text{PdX}_2$, and $\text{Pd}(\text{OR}^{19})_2$;

said olefin is selected from the group consisting of ethylene, an olefin of the formula $\text{R}^{17}\text{CH}=\text{CH}_2$ or $\text{R}^{17}\text{CH}=\text{CHR}^{17}$, cyclobutene, cyclopentene, and a norbornene;

R^2 and R^5 are each independently aryl or substituted aryl, provided in both R^2 and R^5 at least one of the carbon atoms bound to a carbon atom bound directly to an imino nitrogen atom does not have any hydrogen atoms bound to it;

R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

R^{13} , R^{14} and R^{15} are each independently aryl or substituted aryl;

each R^{17} is independently hydrocarbyl or substituted hydrocarbyl provided that any olefinic bond in said olefin is separated from any other olefinic bond or aromatic ring by a quaternary carbon atom or at least two saturated carbon atoms;

each R^{19} and R^{19} is independently hydrocarbyl, substituted hydrocarbyl, or $R^{21}SO_3^-$;

each R^7 , R^8 , R^9 and R^{10} is independently hydrocarbyl or substituted hydrocarbyl containing from 1 to 20 carbon atoms;

each X is independently halogen or $R^{21}SO_3^-$;

each R^{21} is independently aryl, substituted aryl or perfluoroalkyl;

L^1 and L^2 are independently ligands capable of being displaced by (I), or taken together are a bidentate ligand that is capable of being displaced by (I); and

Y is a relatively noncoordinating anion;

and provided that when said hydrocarbylation compound is other than an alkylaluminum compound containing one or more halogen atoms bound to an aluminum atom or $(R^{20}AlO)_q$, wherein R^{20} is alkyl and q is a positive integer, (II) must be present.

3. The process as recited in claim 1 or 2 wherein said olefin is ethylene.

4. The process as recited in claim 1 or 2 wherein said olefin is norbornene.

5. The process as recited in claim 1 wherein said olefin is cyclopentene.

6. The process as recited in claim 1 or 2 wherein said olefin is a linear α -olefin.

7. The process as recited in claim 1 or 2 wherein a random or block copolymer is produced.

8. The process as recited in claim 1 or 2 wherein said hydrocarbylation compound is MX_mR^n , wherein:

M is Li, Mg, Zn[II], Al or Sn[IV];

each X is independently F, Cl, Br, I, or OR^{12} ;

each R^6 is independently hydrocarbyl containing 1 to 20 carbon atoms;

m is 0 or a positive integer;

n is an integer of 1 or more;

m+n is the valence of M; and

R^{12} is hydrocarbonyl containing 1 to 20 carbon atoms.

9. The process as recited in claim 1 or 2 wherein Y is BAF, BF₄, B(C₆F₅)₄, SbF₆ or PF₆.


5 10. The process as recited in claim 1 or 2 wherein R², R³, R⁴ and R⁵ are:

R ²	R ³	R ⁵	R ⁵
2,6-i-PrPh	H	H	2,6-i-PrPh
2,6-i-PrPh	Me	Me	2,6-i-PrPh
2,6-i-PrPh	An	An	2,6-i-PrPh
2,6-MePh	H	H	2,6-MePh
2,6-i-PrPh	Me	Me	2,6-i-PrPh
2,6-i-PrPh	H	H	2,6-i-PrPh
2,6-MePh	H	H	2,6-MePh
2,6-i-PrPh	H	H	2,6-i-PrPh
2,6-i-PrPh	Me	Me	2,6-i-PrPh
2,6-MePh	H	H	2,6-MePh
2,6-EtPh	Me	Me	2,6-EtPh
2,4,6-MePh	Me	Me	2,4,6-MePh
2,6-MePh	Me	Me	2,6-MePh
2,6-i-PrPh	An	An	2,6-i-PrPh
2,6-MePh	An	An	2,6-MePh
2-t-BuPh	An	An	2-t-BuPh
2,5-t-BuPh	An	An	2,5-t-BuPh
2,4,6-MePh	An	An	2,4,6-MePh
2-Cl-6-MePh	Me	Me	2-Cl-6-MePh
2,6-Cl-4-OMePh	Me	Me	2,6-Cl-4-OMePh
2,6-Cl-4-OMePh	An	An	2,6-Cl-4-OMePh
2-i-Pr-6-MePh	An	An	2-i-Pr-6-MePh
2-i-Pr-6-MePh	Me	Me	2-i-Pr-6-MePh
2,6-t-BuPh	H	H	2,6-t-BuPh
2,6-t-BuPh	Me	Me	2,6-t-BuPh
2,6-t-BuPh	An	An	2,6-t-BuPh
2-t-BuPh	Me	Me	2-t-BuPh.

11. The process as recited in claim 1 or 2 wherein said temperature is about 25°C to about 100°C.

12. The process as recited in claim 1 or 2 wherein (II) is $(C_6F_5)_3B$.

13. The process as recited in claim 1 wherein said complex is



wherein:

M is Ni or Pd;

T^1 and T^2 are each independently halogen, R^7CO_2 , $R^8COCH=C(O)R^8$, or OR^{18} ;

R^2 and R^5 are each independently aryl or substituted aryl, provided in both R^2 and R^5 at least one of the carbon atoms bound to a carbon atom bound directly to an imino nitrogen atom does not have any hydrogen atoms bound to it;

R^3 and R^4 are each independently hydrogen, hydrocarbyl, substituted hydrocarbyl, or R^3 and R^4 taken together are hydrocarbylene or substituted hydrocarbylene to form a carbocyclic ring;

each R^{18} is independently hydrocarbyl; and

each R^7 and R^8 is independently hydrocarbyl or substituted hydrocarbyl containing from 1 to 20 carbon atoms.

14. The process as recited in claim 1 wherein a molar ratio of (II):Pd or Ni is about 0.5 to about 10, and a molar ratio of hydrocarbylation compound: Pd or Ni is about 0.5 to about 20.

15. The process as recited in claim 2 wherein:

when (II) is present a molar ratio of (II):Pd or Ni is about 0.5 to about 10, and a molar ratio of hydrocarbylation compound: Pd or Ni is preferably about 0.5 to about 20; and

when (II) is not present said molar ratio of hydrocarbylation compound: Pd or Ni is about 0.5 to about 200.

16. The process as recited in claim 13 wherein T¹ and T² are chlorine or bromine.

17. The process as recited in claim 1, 2 or 13 wherein:

said hydrocarbylation compound is MX_mR_n⁶,

wherein:

10 M is Li, Mg, Zn[II], Al or Sn[IV];
each X is independently F, Cl, Br, I, or OR¹²;
each R⁶ is independently hydrocarbyl containing
1 to 20 carbon atoms;
m is 0 or a positive integer;
15 n is an integer of 1 or more;
m+n is the valence of M; and
R¹² is hydrocarbyl containing 1 to 20 carbon
atoms; and

20 said temperature is about 25°C to about
100°C; and

(II) is (C₆F₅)₃B.

18. The process as recited in claim 1, 2 or 13 wherein:

said hydrocarbylation compound is MX_mR_n⁶;


25 M is Li, Mg, Zn[II], Al or Sn[IV];
each X is independently F, Cl, Br, I, or OR¹²;
each R⁶ is independently hydrocarbyl containing
1 to 20 carbon atoms;
m is 0 or a positive integer;
30 n is an integer of 1 or more;
m+n is the valence of M; and
R¹² is hydrocarbyl containing 1 to 20 carbon
atoms;

35 said temperature is about 25°C to about 100°C;
and

(II) is (C₆F₅)₃B; and

said olefin is one or more of ethylene,
norbornene, cyclopentane, or a linear α-olefin.

INTERNATIONAL SEARCH REPORT

	International Application No. /US 97/12801
--	---

A. CLASSIFICATION OF SUBJECT MATTER IPC 6 C08F4/70 C07F15/04 C07C251/20		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 6 C08F C07F C07C		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	SVOBODA M ET AL: "DIAZADIEN-NICKEL-ALKYLE" JOURNAL OF ORGANOMETALLIC CHEMISTRY, vol. 191, 1 January 1980, pages 321-328, XP000590806 see abstract see page 322, line 3 - line 5 see page 322, line 6 - line 13 see page 323 see page 327 compound III and Versuch zur Oligomerisierung von Butadien <div style="text-align: center; margin-top: 20px;"> --- -/-- </div>	1, 2, 8, 10, 13, 14, 16, 17
<div style="display: flex; justify-content: space-between;"> <input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex. </div>		
<div style="display: flex;"> <div style="flex: 1;"> <p>Special categories of cited documents:</p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="flex: 1;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"&" document member of the same patent family</p> </div> </div>		
Date of the actual completion of the international search <div style="text-align: center; font-weight: bold;">24 November 1997</div>		Date of mailing of the international search report <div style="text-align: center; font-weight: bold;">09/12/1997</div>
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer <div style="text-align: center; font-weight: bold;">Fischer, B</div>

INTERNATIONAL SEARCH REPORT

Patent Application No.
PCT/US 97/12801

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	JOHNSON L K ET AL: "NEW PD(II)- AND NI(II)-BASED CATALYSTS FOR POLYMERIZATION OF ETHYLENE AND ALPHA-OLEFINS" JOURNAL OF THE AMERICAN CHEMICAL SOCIETY, vol. 117, 14 June 1995, page 6414/6415 XP000644782 cited in the application see the whole document see in supplementary material (29 pages), page 4, compound 5e page 9, polymerization of ethylene 5e/MAO page 10, polymerization of 1-hexene 5e/MAO ---	2,3,6,8, 10,11, 13, 16-18,22
P,X	WO 96 23010 A (DU PONT) 1 August 1996 see page 148 - page 151; examples 10-14 see page 159; example 39 see page 183; example 83 see page 231; example 154 see page 263; example 210 see page 289; example 254 ---	1-3,5,6, 10,11, 13,14, 16-18,22
A	R. VAN ASSELT ET AL: "Synthesis and Characterization of rigid bidentate nitrogen ligands..." RECL.TRAV. CHIM. PAYS-BAS, vol. 113, 1994, pages 88-98, XP002047441 see page 89 (Ar-BIAN)NiBr ₂ (2) see page 92, column 1, Scheme 1: Synthesis of Ar-BIAN ligands see page 93; table 1 -----	19-21

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/12801

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9623010 A	01-08-96	AU 5020896 A	14-08-96
		EP 0805826 A	12-11-97
		NO 973310 A	23-09-97
<hr/>			

THIS PAGE BLANK (USPTO)